

Abrasion Resistance

Series: Taconic Slate Color - Sizes: 25106 - 6x6, 12x12, 18x18

ANSI Tile Type: Porcelain Floor Tile

Glaze Finish: Glazed

Reported by: John Heckman

Report Date: August 13, 2009

Procedure: ASTM C1027

<u>Description:</u> Tiles are placed on an ASTM compliant abrasion tester and abraded by the rotation of an abrasive media acting on the tiles.

Revolutions to Visible Abrasion	Class	Classification
100	0	Not recommended for floors
150	1	Light Residential
600	2	Residential
750 or 1500	3	Heavy Residential/Lt Commercial
2100, 6000, or 12000	4	Commercial
12000+ and stain test	5	Heavy Commercial

Results:

ults:	Revolutions	Class	Classification
	1500	3	Heavy Residential/Lt Commercial

Dan Marvin

Director of Quality Assurance



Breaking Strength

Col	Series: Taconic Slate or - Sizes: 25106 - 6x6, 12x12, 1	8x18	Glaze Finish: Glazed ANSI Tile Type: Porcelain Floor Tile	
Reported by: John Heckman			Report Date: August 13, 2009	
Procedure:	ASTM C648			
Description:	Tiles are placed on a standard breaking strength machine and stressed until broken. The maximum force achieved before breaking is the strength of the sample. Reported value is the average of 10 pieces.			
Requirement:	ANSI standards require a minin	num breaking strength for t	tile of this type to be equal or greater than 250 lbs	
Results:	Average:	450 lbs	Pass	

Dan Marvin

Director of Quality Assurance



Moh's Hardness

Series: Taconic SlateGlaze Finish: GlazedColor - Sizes: 25106 - 6x6, 12x12, 18x18ANSI Tile Type: Porcelain Floor TileReported by: John HeckmanReport Date: August 13, 2009

Procedure: EN 101

Description: Tiles are tested by moving a mineral tipped stylus across the surface and looking for a scratch to be produced during 4 test cycles. The scale is calibrated using increasingly more dense minerals.

Classification:

Moh's Scale	Mineral
5	Apatite
5.5	Opal
6	Turquoise
6.5	Jade
7	Quartz
7.5	Emerald
8	Topaz
8.5	Alexandrite
9	Ruby
10	Diamond

Results:

Moh's Scale	Mineral
7	Quartz

Dan Marvin

Director of Quality Assurance



Water Absorption

Series: Taconic SlateGlaze Finish: GlazedColor - Sizes: 25106 - 6x6, 12x12, 18x18ANSI Tile Type: Porcelain Floor TileReported by: John HeckmanReport Date: August 13, 2009

Procedure: ASTM C373

<u>Description:</u> Dried samples are boiled for 5 hours, then allowed to sit for 24 hours in distilled water. The percent water absorption is calculated by the difference in weight between the wet tile and the dry tile.

Classification:

Scale Classification	
≤0.5%	Porcelain
0.5% - 3.0%	Vitreous
3.0% - 7.0%	Semi-Vitreous
7.0% - 20.0%	Non-Vitreous

Results:

Result	Classification
≤0.5%	Porcelain

Third Party Certification: This product is Certified Porcelain by the Porcelain Tile Certification Agency



Dan Marvin

Director of Quality Assurance



Static Coefficient of Friction

Series: Taconic SlateGlaze Finish: GlazedColor - Sizes: 25106 - 6x6, 12x12, 18x18ANSI Tile Type: Porcelain Floor TileReported by: John HeckmanReport Date: August 13, 2009

Procedure: ASTM C1028

<u>Description:</u> Tiles are tested wet and dry. A neolite 'heel' is weighted with a 50 lb weight and force is applied until assembly begins to move. The peak force is recorded and the coefficient of friction is calculated versus a standard tile. Reported averages are from three separate test samples from the same lot

Results:

Wet Average	0.6
Dry Average	0.8

Dan Marvin

Director of Quality Assurance



Percentage of Recycled Content

Series: Taconic Slate	Glaze Finish: Glazed
Color - Sizes: 25106 - 6x6, 12x12, 18x18	ANSI Tile Type: Porcelain Floor Tile
Reported by: John Heckman	Report Date: December 8, 2010

Procedure: Calculated per LEED for New Construction and Major Renovations Rating System, April 2009

Description: The amount of pre- and post-consumer waste is calculated based on a percentage of the body by weight

Results: Pre-consumer RMC Post-consumer RMC



Dan Marvin

Director of Quality Assurance

** Values are offered in good faith as being accurate and typical of normal production.

Due to natural variation of raw materials and manufacturing processes, the values of tile purchased for any particular

installation may vary from these numbers. Buyer should evaluate suitability and safety of any product prior to installation. No warranty of any kind, expressed or implied, is made with respect to the information contained herein.



Bond Strength

	Series: Taconic Slate r - Sizes: 25106 - 6x6, 12x12, 18x orted by: John Heckman	18 ANS	aze Finish: Glazed I Tile Type: Porcelain Floor Tile eport Date: August 13, 2010	
Procedure:	ASTM C482			
Description:	Tiles are bonded with a standard mortar to a standard cement block. Force is applied to the tile until the bond fails. Results are average force required for failure for 5 pieces.			
Requirement:	ANSI standards require a minimum	m bond strength for tile of this	type to be equal to or greater than 50 PSI	
<u>Results:</u>	Average:	377 PSI	Pass	

Dan Marvin

Director of Quality Assurance