












## TECHNICAL SPECS

TECHNICAL DATA	STANDARD NORM	STANDARD VALUE	ROCK LIMESTONE READINGS-POLISHED
 <b>LENGTH</b>	EN ISO 10545-2	±0.6%	-0.02%~0%
 <b>WIDTH</b>	EN ISO 10545-2	±0.6%	-0.02%~0%
 <b>THICKNESS</b>	EN ISO 10545-2	±5%	-0.80%~+0.80%
 <b>PLANARITY/ SURFACE FLATNESS</b>	EN ISO 10545-2	±0.5%	±0.03%
 <b>WATER ABSORPTION</b>	EN ISO 10545-3	≅ 0.5%	≅ 0.3%
 <b>BREAKING STRENGTH</b>	EN ISO 10545-4	≅ 1300N	≅ 2084N
 <b>MODULUS OF RUPTURE</b>	EN ISO 10545-4	≅ 35N/mm <sup>2</sup>	≅ 42.2N/mm <sup>2</sup>
 <b>STAIN RESISTANCE</b>	EN ISO 10545-14	No visible staining	No visible staining
 <b>RESISTANCE TO ABRASION</b>	EN ISO 10545-7	Resistance to surface abrasion of glazed tiles intended for use on floors:abrasion class and cycles passed	Class 3 750 cycles
 <b>FROST RESISTANCE</b>	EN ISO 10545-12	No damage	No damage
 <b>CHEMICAL RESISTANCE</b>	EN ISO 10545-13	No damage	No damage GA/ GLA/ GHA